

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A01N 59/00	A2	(11) International Publication Number: WO 98/41095 (43) International Publication Date: 24 September 1998 (24.09.98)
(21) International Application Number: PCT/CA98/00102 (22) International Filing Date: 17 February 1998 (17.02.98) (30) Priority Data: 08/818,869 17 March 1997 (17.03.97) US (71) Applicant (for all designated States except US): WESTAIM TECHNOLOGIES INC. [CA/CA]; 10102 - 114 Street, Fort Saskatchewan, Alberta T8L 3W4 (CA). (72) Inventors; and (75) Inventors/Applicants (for US only): BURRELL, Robert, Edward [CA/CA]; 52055, R.R. 221, Sherwood Park, Alberta T8E 1C6 (CA). PRECHT, Roderick, John [CA/CA]; 13143 - 34 Street, Edmonton, Alberta T5A 3K1 (CA). (74) Agent: McKAY-CAREY, Mary, Jane; McKay-Carey & Company, 2125 Commerce Place, 10155 - 102nd Street, Edmonton, Alberta T5J 4G8 (CA).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>Without international search report and to be republished upon receipt of that report.</i>
(54) Title: ANTI-MICROBIAL COATINGS HAVING INDICATOR PROPERTIES AND WOUND DRESSINGS		
(57) Abstract <p>Multilayer anti-microbial materials formed to produce an interference colour, and thus an indicator of anti-microbial effect, are provided. The materials include a partly reflective base layer and a partly reflective, partly transmissive top layer balanced to produce an interference colour. The top layer is formed from an anti-microbial metal with atomic disorder. Dissolution or a change in composition of the top layer on contacting an alcohol or electrolyte causes a change in optical path length so as to produce a change in the interference colour of the material. Multilayer, laminated wound dressings are also provided. The dressing includes a first and second layer, and preferably a third layer. The first and third layers are formed of perforated, non-adherent materials and most preferably carry an anti-microbial coating as above. The second layer is sandwiched between the first and third layers and is formed of an absorbent material. At least one of the layers is formed from a plastic material. The layers are laminated together by ultrasonic welds spaced intermittently on the dressing to allow the dressing to be cut to size with delaminating.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

Anti-Microbial Coatings Having Indicator Properties and Wound Dressings

FIELD OF THE INVENTION

The invention relates to anti-microbial coatings formed from one or more anti-microbial metals and to multilayer laminated wound dressings.

BACKGROUND OF THE INVENTION

Burns and related wounds present a serious problem in infection control. Noble metal ions such as silver and gold ions are known for their anti-microbial activity and have been used in medical care for many years to prevent and treat infection. Water soluble silver nitrate has been widely used as an astringent and as a potent anti-microbial solution. For example, 10% silver solution preparations are applied directly to ulcers of the mouth; dressings wetted with 0.5% silver nitrate solutions are used to cover second and third degree burns, especially to protect against gram negative infections; and drops of a 1% silver nitrate solution in the eye is still a legally required treatment in many areas of the world for prophylaxis of ophthalmia neonatorum.

The anti-microbial effect of these known silver nitrate solutions appears to be directly related to the concentration of the silver ions. Unfortunately, water soluble silver nitrate solutions provide very little residual activity due to the reactivity of silver ions with chloride, etc. in body fluids. To compensate for this lack of in use longevity, soluble silver solutions, such as silver nitrate, are used at far higher concentrations (3000 to 3500 mg/L) than are required for bacterial control (2 to 5 mg/L) in an effort to extend the duration of the antimicrobial effect. As a result, the solution can have irritating and astringent effects on wounds. For instance 1% solutions used prophylactically for ophthalmia neonatorum must be followed in a few seconds with a 0.85% sodium chloride rinse to prevent conjunctivitis. Burn wound treatment in current use for second degree burns employs 0.5% silver nitrate solutions which must be added frequently throughout the day (usually 12 times daily) in order to replenish the active Ag^+ ion. Also in use are silver sulphadiazine creams, which need frequent reapplication and scraping to remove the debris and chemical barrier, and which may also cause sensitivity or allergic reaction to the sulpha component.

Significant improvements to minimize adverse properties have been sought since the turn of the century. Some efforts have focussed on the use of colloidal solutions of insoluble, poorly ionized salts such as oxide complexes with proteins to reduce the rate of release of

1 silver ions. Other efforts focussed on producing silver in an activated form, for example by
2 depositing it on porous carbon to provide slower release of silver ions, or by activating the
3 silver after deposition, for example by treatment with strong oxidizing agents. Still other
4 efforts were directed at electrical activation of the silver coatings to drive the release of silver,
5 or depositing with an electrochemically different, more noble metal so as to use dual metal
6 galvanic action as the driving force to release silver ions. To date, improvements in anti-
7 microbial agents derived from anti-microbial metals such as silver, and wound treatment
8 procedures using same are sought to improve the anti-microbial efficacy of the metal ions, to
9 reduce the frequency of the application of the anti-microbial agent, and to improve infection
10 control in wound treatment. Also needed is a visible indicator of the anti-microbial activity
11 and effect, so as to minimize over application of the anti-microbial agents and unnecessary
12 wound dressing removal, and thus improve patient comfort and minimize sensitivity reactions
13 to anti-microbial metals.

14 Applicants have developed anti-microbial materials which provide efficacious and
15 sustainable anti-microbial effect. Such materials are described in, for example US Patent
16 5,454,886, issued October 3, 1995, to Burrell et al. The materials are formed as powders,
17 foils, flakes, coatings or thin films from one or more anti-microbial metals so as to contain
18 atomic disorder.

19 SUMMARY OF THE INVENTION

20 The inventors made a number of surprising discoveries when working on
21 improvements to the anti-microbial materials formed with atomic disorder described in their
22 previous patent applications. Firstly, they discovered that a thin film of an anti-microbial
23 metal material on a reflective base layer coating, such as a reflective silver coating, was
24 capable of producing an interference colour. By altering the refractive index and/or the
25 thickness of the top layer, different, discernible interference colours were produced.
26 Secondly, they discovered that if the top anti-microbial metal layer was formed with atomic
27 disorder so as to produce an anti-microbial effect when exposed to alcohol or electrolyte,
28 sharp interference colours were produced, providing a useful indicator of activation (release
29 of ions etc.) from medical devices and the like carrying such a coating. Even minor
30 dissolution or composition changes of the top layer of the coating, such as a fingertip touch,
31 was discovered to cause a detectable colour change. Thirdly, they discovered that a single
32 layer of an anti-microbial metal formed with atomic disorder could be produced with an

1 initial colour which changed on contacting an alcohol or electrolyte so as to generate an
2 interference colour which was different from the initial colour. Without being bound by the
3 same, it is believed that contacting the atomically disordered material forms a thin layer at the
4 top of the material (hereinafter termed an "in situ generated top layer") which has a
5 composition different enough from the underlying base layer that it is capable of providing an
6 interference colour. Thus, the present invention extends to a method of indicating exposure
7 of multilayer anti-microbial material formed with atomic disorder to an alcohol or electrolyte
8 through the use of interference colours.

9 In one broad aspect, the invention provides a multilayer anti-microbial material
10 comprising a) a base layer of a partly reflective material capable of generating an interference
11 colour when covered with a partly reflective, partly light transmissive top layer; and b) a top
12 layer formed over said base layer, said top layer being a partly reflective, partly light
13 transmissive thin film containing at least one anti-microbial metal and having a thickness
14 such that an interference colour is produced, said top layer having a refractive index different
15 from that of the base layer, and the anti-microbial metal being formed with sufficient atomic
16 disorder such that the top layer, in contact with an alcohol or water based electrolyte, releases
17 ions, atoms, molecules or clusters of the anti-microbial metal into the alcohol or water based
18 electrolyte at a concentration sufficient to provide a localized anti-microbial effect on a
19 sustainable basis. The invention extends to anti-microbial materials in which the top layer is
20 formed above the base layer by such techniques as vapour deposition, and to materials having
21 an in situ generated top layer.

22 The base layer might be provided as a substrate (ex. medical device) which is partly
23 reflective such that it can provide an interference colour when covered with a partly
24 reflective, partly transmissive top layer. Preferably the base layer is formed from a metal
25 selected from Ag, Au, Pt, Pd, Cu, Ta or Al, with Au, Ag, Pt, Pd and Cu being most preferred.
26 Preferably both the top and base layers are formed from anti-microbial metals formed with
27 atomic disorder. The top layer is most preferably formed from Au or Ag.

28 Most preferably, the top layer is a composite material formed by depositing the anti-
29 microbial metal in a matrix with atoms or molecules of a different material, wherein the
30 different material provides atomic disorder in the matrix. The different material may be a
31 biocompatible metal such as Ta, Ti, Nb, V, Hf, Zn, Mo, Si or Al, or oxides, nitrides, carbides,
32 borides, halides, sulphides or hydrides of such biocompatible metals. Alternatively, the

1 different material may be atoms or molecules absorbed or trapped from the atmosphere used
2 in a vapour deposition process, including oxygen, nitrogen, hydrogen, boron, sulphur or
3 halogens. As a further alternative, the different material may be an oxide, nitride, carbide,
4 boride, halide, sulphide or hydride of an anti-microbial metal. Most preferably, the top layer
5 is formed with Ag as the matrix metal, and either or both of silver oxide and absorbed or
6 trapped oxygen as the different material.

7 The base layer, when provided as a coating on a substrate, is preferably at least 25 nm
8 thick and more preferably at least 60 nm thick. If formed from an atomically disordered anti-
9 microbial metal, the base layer is preferably between about 300 and 2500 nm thick so as to
10 provide a prolonged anti-microbial effect after the top layer is dissolved. The top layer is
11 preferably less than 400 nm thick and is more preferably between 5 and 210 nm thick. Most
12 preferably, the top layer is between 40 and 160 nm thick.

13 The invention also extends to a process for producing a multilayer anti-microbial
14 material capable of indicating exposure to an alcohol or a water based electrolyte. The
15 process includes a) providing a base layer of a partly reflective material capable of generating
16 an interference colour when covered with a partly reflective, partly light transmissive top
17 layer; and b) providing a top layer over said base layer, said top layer being a partly
18 reflective, partly light transmissive thin film containing at least one anti-microbial metal and
19 having a thickness such that an interference colour is produced, said top layer having a
20 refractive index different from that of the base layer, and said anti-microbial metal being
21 formed with sufficient atomic disorder such that the top layer, in contact with an alcohol or
22 water based electrolyte, releases ions, atoms, molecules or clusters of the anti-microbial metal
23 into the alcohol or water based electrolyte at a concentration sufficient to provide a localized
24 anti-microbial effect on a sustainable basis. The top layer can be provided by depositing it
25 above the base layer, for instance by vapour deposition, or the top layer can be provided as an
26 in situ generated top layer. In either process, a colour change occurs on contact with an
27 alcohol or water based electrolyte so as to indicate activation of the material.

28 The inventors also discovered, when working with wound dressings materials that
29 multilayer wound dressings could be laminated together with the use of ultrasonic welding at
30 intermittent locations, to produce a wound dressing which could be conveniently cut to size,
31 without causing delamination of the layers, and without having to resort to the use of
32 stitching or adhesives to bind the layers together. The presence of the ultrasonic welds at

1 intermittent locations on the dressing was surprisingly advantageous over stitched dressings
2 or the use of adhesives, since the ultrasonically welded dressings were found to have
3 excellent conformability properties (i.e. ability to conform to wound and skin contours). In
4 wound dressings having one or more perforated layers to allow for fluid penetration, the
5 ultrasonic welds were also found to only minimally interfere with penetrability properties of
6 the dressings. Importantly, when wound dressings were coated with anti-microbial metal
7 coatings of this invention, that is dressings which included a coating of one or more layers of
8 an anti-microbial metal formed with atomic disorder, ultrasonic welding to laminate layers of
9 the wound dressing was found not to inhibit anti-microbial activity. Atomic disorder in a
10 material is easily removed when heat is applied to the material, since heat can anneal out
11 crystalline defects.

12 Thus, in another broad aspect, the invention provides a multilayer, laminated wound
13 dressing, including:

- 14 a first, wound facing layer formed of a perforated, non-adherent material;
- 15 a second layer laminated to the first layer, and being formed of an absorbent material;
- 16 an optional third layer laminated to one or both of the first and second layers;
- 17 at least one of the first, second and optional third layers, being formed from a plastic
18 material; and
- 19 the first, second and optional third layers being laminated together by ultrasonic welds
20 spaced intermittently on the dressing so as to allow the dressing to be cut down in size
21 without causing delamination.

22 The wound dressing is preferably formed with an anti-microbial coating which is most
23 preferably the multilayer anti-microbial material set out above, so as to provide an
24 interference colour indicator of activation on contacting an alcohol or a water based
25 electrolyte.

26 As used herein and in the claims, the terms and phrases set out below have the
27 meanings which follow.

28 "Metal" or "metals" includes one or more metals whether in the form of substantially
29 pure metals, alloys or compounds such as oxides, nitrides, borides, sulphides, halides or
30 hydrides.

31 "Anti-microbial metals" are metals whose ions have an anti-microbial effect.
32 Preferably, the metal will also be biocompatible. Preferred anti-microbial metals include Ag,

1 Au, Pt, Pd, Ir (i.e. the noble metals), Sn, Cu, Sb, Bi and Zn.

2 "Biocompatible" means non-toxic for the intended utility. Thus, for human utility,
3 biocompatible means non-toxic to humans or human tissues.

4 "Anti-microbial effect" means that atoms, ions, molecules or clusters of the anti-
5 microbial metal (hereinafter "species" of the anti-microbial metal) are released into the
6 alcohol or electrolyte which the material contacts in concentrations sufficient to inhibit
7 bacterial (or other microbial) growth in the vicinity of the material. The most common
8 method of measuring anti-microbial effect is by measuring the zone of inhibition (ZOI)
9 created when the material is placed on a bacterial lawn. A relatively small or no ZOI (ex. less
10 than 1 mm) indicates a non useful anti-microbial effect, while a larger ZOI (ex. greater than 5
11 mm) indicates a highly useful anti-microbial effect. One procedure for a ZOI test is set out in
12 the Examples which follow.

13 "Sustained release" or "sustainable basis" are used to define release of atoms,
14 molecules, ions or clusters of an anti-microbial metal that continues over time measured in
15 hours or days, and thus distinguishes release of such metal species from the bulk metal, which
16 release such species at a rate and concentration which is too low to achieve an anti-microbial
17 effect, and from highly soluble salts of anti-microbial metals such as silver nitrate, which
18 releases silver ions virtually instantly, but not continuously, in contact with an alcohol or
19 electrolyte.

20 "Atomic disorder" includes high concentrations of: point defects in a crystal lattice,
21 vacancies, line defects such as dislocations, interstitial atoms, amorphous regions, grain and
22 sub grain boundaries and the like relative to its normal ordered crystalline state. Atomic
23 disorder leads to irregularities in surface topography and inhomogeneities in the structure on
24 a nanometer scale.

25 "Normal ordered crystalline state" means the crystallinity normally found in bulk
26 metal materials, alloys or compounds formed as cast, wrought or plated metal products. Such
27 materials contain only low concentrations of such atomic defects as vacancies, grain
28 boundaries and dislocations.

29 "Diffusion", when used to describe conditions which limit diffusion in processes to
30 create and retain atomic disorder i.e. which freeze-in atomic disorder, means diffusion of
31 atoms and/or molecules on the surface or in the matrix of the material being formed.

32 "Substrate" means any surface, usually that of a medical device, which is itself partly

1 reflective, or which can be coated with a partly reflective metal coating by such techniques
2 vapour deposition including evaporation or physical vapour deposition. In this application, it
3 should be understood that when it is stated that a reflective base layer is provided on a
4 substrate, it does not mean that every substrate needs to have such a layer formed thereon, but
5 is meant to include a substrate which is inherently reflective, such as for instance reflective
6 plates or instruments formed of polymers, metals or dielectrics, such that it can provide an
7 interference colour.

8 "Medical device" means any device, appliance, fixture, fibre, fabric or material
9 intended for a medical, health care or personal hygiene utility, including, without limitation
10 orthopaedic pins, plates, implants, tracheal tubes, catheters, insulin pumps, wound closures,
11 drains, shunts, dressings, connectors, prosthetic devices, pacemaker leads, needles, dental
12 prostheses, ventilator tubes, surgical instruments, wound dressings, incontinent pads, sterile
13 packaging clothing footwear, personal hygiene products such as diapers and sanitary pads,
14 and biomedical/biotechnical laboratory equipment such as tables, enclosures and wall
15 coverings and the like. Medical devices may be made of any suitable material, for example
16 metals, including steel, aluminum and its alloys, latex, nylon, silicone, polyester, glass,
17 ceramic, paper, cloth and other plastics and rubbers. For indwelling medical devices, the
18 device will be made of a bioinert or biocompatible material. The device may take on any
19 shape dictated by its utility, ranging from flat sheets to disc, rods and hollow tubes. The
20 device may be rigid or flexible, a factor dictated by its intended utility.

21 "Alcohol or water based electrolyte" is meant to include any alcohol or water based
22 electrolyte that the anti-microbial materials of the present invention might contact in order to
23 activate (i.e cause the release of species of the anti-microbial metal) into same. The term is
24 meant to include alcohols, water, gels, fluids, solvents, and tissues containing water,
25 including body fluids (for example blood, urine or saliva), and body tissue (for example skin,
26 muscle or bone).

27 "Colour change" is meant to include changes of intensity of light under
28 monochromatic light as well as changes of hue from white light containing more than one
29 wavelength.

30 An "interference colour" is produced when light impinges on two or more partly
31 reflective surfaces separated by a distance which bears the right relationship to the
32 wavelength of the light to be removed by destructive interference.

“Partly reflective” when used to describe the base or top layer materials, means that the material has a surface which reflects a portion of incident light, but which also transmits a portion of the incident light. Reflection occurs when a ray of incoming light encounters a boundary or interface characterized by a change in refractive index between two media. For the top layer of the anti-microbial materials of this invention, that interface is with air. For the base layer, the interface is with the top layer. The reflectance of the base and top layers is balanced so as to generate an interference colour.

“Partly light transmissive” when used to describe a thin film of the top layer material means that the thin film is capable of transmitting at least a portion of incident visible light through the thin film.

“Detectable” when used to describe a colour change means an observable shift in the dominant wavelength of the reflected light, whether the change is detected by instrument, such as a spectrophotometer, or by the human eye. The dominant wavelength is the wavelength responsible for the colour being observed.

"Wound" means cut, lesion, burn or other trauma to human or animal tissue requiring a wound dressing.

“Wound dressing” means a covering for a wound.

DESCRIPTION OF THE DRAWINGS

Figure 1 is a schematic sectional figure of a coloured anti-microbial coating of this invention showing the generation of an interference colour;

Figure 2 is a schematic sectional figure of a three layer wound dressing in accordance with the present invention.

DESCRIPTION OF THE PREFERRED EMBODIMENTS

1. Multilayer Anti-Microbial Materials With Interference Colour

The invention provides anti-microbial materials formed with at least two layers, a base layer and a top layer, so as to produce an interference colour. Both layers are partly reflective; the top layer is partly light transmissive. The top layer is a thin film containing at least one anti-microbial metal formed with sufficient atomic disorder such that the top layer, in contact with an alcohol or water based electrolyte, releases ions, atoms, molecules or clusters of the anti-microbial metal at a concentration sufficient to provide a localized anti-

1 microbial effect on a sustainable basis. In this way, the top layer, in contact with the alcohol
2 or electrolyte, will undergo a change in optical path length, either by a change in thickness
3 resulting from some dissolution, or through a change in the refractive index of the top layer
4 resulting from a change in the composition of a newly formed thin layer formed on the top
5 layer. Either or both of these results are sufficient to cause a detectable colour change, thus
6 providing an indicator that the top coating has been activated.

7 The generation of interference colours is known in the art for decorative effects,
8 diffraction gratings and diagnostic assay techniques, and thus the properties of at least two
9 layers of materials necessary to generate an interference colour, that is the balance of
10 reflectance, transmittance, layer thicknesses, and refractive indices of the layers, are generally
11 well known in the art. The prior art has generally taught one to anodize a metal to produce a
12 thin layer of a generally transparent oxide above a reflective base metal (see for example US
13 5,124,172 issued June 23, 1992 to Burrell et al.). Other prior art has taught sputter coating
14 certain reflective metals with oxides of same or different metals in order to generate
15 interference colours (see for example US 4,702,955, issued October 27, 1987, to Allred et
16 al.). However, not all metals are easily anodizable. Furthermore, the art teaches that
17 sputtering of such important anti-microbial metal oxides as silver oxide, is not possible
18 without decomposition (see for example US 4,728,323 issued March 1, 1988, to Matson).
19 Thus, novel procedures for producing anti-microbial materials capable of producing
20 interference colours and an indication of generation of an anti-microbial effect, are set out
21 herein.

22 The anti-microbial materials of this invention and the generation of an interference
23 colour are shown schematically in Figure 1. The material includes a base layer 2 and a top
24 layer 4 over the base layer 2. The base and top layers 2, 4 are generally provided on a
25 substrate 6, such as the surface of a medical device. However, if the substrate is itself partly
26 reflective, the substrate can serve as the base layer. Both the base layer 2 and the top layer 4
27 are formed from a partly reflective material. In this way, at least a portion of the incoming
28 light is reflected from the surface of the layer while another portion is transmitted through the
29 layer. The top layer 4 is partly light transmissive to allow incident light to reach the interface
30 with the base layer 2. The top layer 4 thus cannot approximate 100% reflectivity, such as in
31 pure Al or Ag, or interference colours cannot be generated, as is well known in the art. The
32 materials for layers 2, 4 should be balanced in their reflectances in order to generate an

1 interference colour. Generally, the top layer 4 is deposited as a thin film having a thickness
2 which maintains adequate transmittance to generate an interference colour. Furthermore, the
3 refractive index for the materials in layers 2, 4 is different, accomplished by differences in
4 their actual or effective compositions. For instance different materials in the two layers will
5 result in the materials having different actual refractive indexes. However, if it is desired to
6 make the layers 2, 4 from the same material, the layers can be deposited with different
7 porosities or different levels/types of atomic disorder, in order to achieve different effective
8 compositions, and thus different refractive indexes.

9 In this manner, in Figure 1, incoming light A reflects off the interface 7 of the base
10 and top layers 2, 4. Incoming light B reflects from the interface 8 of the top layer 4 with air,
11 and interferes with the light reflected from the interface 7, so as to generate an "interference
12 colour" C. The particular colour which is generated and its brightness will depend on the
13 properties of the layers 2, 4, most importantly on the composition of the layers, which
14 determines its transmittance and absorption properties, along with its refractive index, and on
15 the thickness of the layers. Generally, it is desirable to generate first and second order
16 interference colours, by limiting the thickness of the base layer and top layers to minimize the
17 number of internal reflections. First and second order interference colours are generally
18 brighter than third and fourth order etc. colours, making them more aesthetically pleasing,
19 more consistently reproducible in manufacturing, and more susceptible to detectable colour
20 change on variations in thickness on dissolution of even a minor amount of the top layer 4.

21 The property which determines the particular colour which is generated is the
22 effective optical thickness of the top layer 4, that is the product of the refractive index of the
23 top layer material and the actual thickness of the top layer 4. Thus the colour which is
24 desired can be altered by changing the actual thickness of the top layer 4 or its refractive
25 index.

26 In accordance with the invention, the base layer 2 is a partly reflective material
27 capable of generating an interference colour when covered with a partly reflective, partly
28 transmissive top layer 4. Reflective materials such as polymers, dielectrics or metals may be
29 used in the base layer. To achieve the desired level of reflectance, the base layer 2 may be
30 coated with an additional layer (not shown) to change its reflectance. For instance, a
31 reflective plastic plate might be coated with a discontinuous (islands) or continuous thin
32 coating of a reflective metal such as silver to produce a base layer whose average reflectance

1 could be better balanced with that of the top layer to generate the desired interference colour
2 effect. Preferably, the material in the base layer 2 is a reflective metal. Such metals are
3 known in the art and include, for example one or more of the valve metals, e.g. Ta, Nb, Ti, Zr
4 and Hf, as well as transition metals such as Au, Ag, Pt, Pd, Sn, Cu, V, W and Mo, or the
5 metal Al. More preferably, the base material is formed from Ag, Au, Pt, Pd, Cu, Ta and Al.
6 Use of a metal such as tantalum as the base layer 2 may cause reduction of oxide containing
7 materials in the top layer 4. To avoid this, a barrier layer (not shown), such as tantalum oxide
8 formed by anodizing at least a portion of the top surface of the Ta metal, should be included
9 above a tantalum layer. Preferred metals for the base layer 2 are the anti-microbial metals
10 Au, Ag, Pt, Pd, Sn and Cu, most preferably Au, Pt and Ag, in a partly reflective form.

11 The base layer 2 may be formed by known techniques, such as the vapour deposition
12 techniques of evaporation or physical vapour deposition. Preferably, the base layer 2 is
13 formed as a thin film by physical vapour deposition with atomic disorder, as set out below
14 and in the inventors' previous patent applications, for example US 5,454,889, in order to
15 produce a sustainable anti-microbial effect when the base layer is ultimately exposed to an
16 alcohol or water based electrolyte. The thickness of the base layer 2 is generally not critical,
17 provided that it is partly reflective. Preferred thicknesses will vary widely with the material
18 composition and the desired colour. However, in that the layer 2 is preferably a thin film
19 formed by physical vapour deposition techniques, it should be at least about 25 nm thick to
20 create a useful colour. To generate first and second order interference colours and to produce
21 an anti-microbial effect in accordance with the preferred aspects of the invention, the base
22 layer 2 should be greater than 60 nm thick, more preferably 300 to 2500 nm thick, and most
23 preferably 600 to 900 nm thick.

24 The top layer 4 is formed of a partly reflective, partly light transmissive thin film
25 containing at least one anti-microbial metal formed with atomic disorder so as to produce a
26 sustainable anti-microbial effect, and ultimate colour change, when exposed to an alcohol or a
27 water based electrolyte. The anti-microbial metal is preferably one or more of Ag, Au, Pt, Pd,
28 Ir, Sn, Cu, Sb, Bi, and Zn in a partly reflective, partly transmissive form. More preferably,
29 the anti-microbial metal is Ag, Au, Pt, Pd or Cu. The thickness of the top layer 4 formed
30 from these metals is preferably less than 400 nm in order to maintain the preferred level of
31 light transmission. The desired thickness will vary with the composition of the top layer 4,
32 and with the desired end colour and colour change. For first and second order interference

1 colours, the thickness will generally be less than about 400 nm. More preferably, the
2 thickness will range from 5 to 210 nm, most preferably from 10 to 100 nm.

3 The top layer 4 may be a thin film of the base layer material, formed with a different
4 refractive index for instance by altering the deposition conditions to change the porosity,
5 composition and/or degree of atomic disorder in the layers 2, 4.

6 When the base layer 2 is itself formed from an anti-microbial metal with atomic
7 disorder, the top layer 4 may be provided as an in situ generated top layer by virtue of its
8 thickness and/or composition changing on contacting an alcohol or water based electrolyte, so
9 as to produce an interference colour which differs from the initial colour of the base layer 2.

10 Most preferably, the top layer 4 is a thin film of a composite material formed by co-,
11 sequentially or reactively depositing an anti-microbial metal in a matrix with atoms or
12 molecules of a different material to create atomic disorder in the matrix, in the manner set out
13 below. The different material is selected from a) biocompatible metals, b) oxygen, nitrogen,
14 hydrogen, boron, sulphur or halogens, or c) an oxide, nitride, carbide, boride, halide, sulphide
15 or hydride of either or both of an anti-microbial metal or a biocompatible metal. Most
16 preferably, the top layer material is a composite material containing silver, and one or both of
17 silver oxide and atoms or molecules containing oxygen trapped or absorbed in the silver
18 matrix. The term "silver oxide" is meant to include any oxide or mixture of oxides of silver.
19 However, the top layer 4 is preferably not formed solely of AgO and/or Ag₂O, since the
20 solubility of these materials is low for providing a useful anti-microbial effect in accordance
21 with the present invention.

22 A) Anti-Microbial Materials Containing Atomic Disorder

23 At least the top layer 4, and preferably also the base layer 2, is formed in a crystalline
24 form from anti-microbial metals with atomic disorder so as to produce an anti-microbial
25 effect. The production of atomic disorder through physical vapour deposition techniques is
26 described in the previous patent applications, including U.S. 5,454,886, and as outlined
27 below.

28 The anti-microbial metal is deposited as a thin metallic film on one or more surfaces
29 of the substrate, typically a medical device, by vapour deposition techniques. Physical
30 vapour techniques, which are well known in the art, all deposit the metal from the vapour,
31 generally atom by atom, onto a substrate surface. The techniques include vacuum or arc
32 evaporation, sputtering, magnetron sputtering and ion plating. The deposition is conducted in

1 a manner to create atomic disorder in the coating as defined hereinabove. Various conditions
2 responsible for producing atomic disorder are useful. These conditions are generally those
3 which one has been taught to avoid in thin film deposition techniques, since the object of
4 most thin film depositions is to create a defect free, smooth and dense film (see for example
5 J.A. Thornton, supra). While such conditions have been investigated in the art, they had not
6 been linked to enhanced solubility of the coatings so-produced prior to Applicants inventions.

7 The preferred conditions which are used to create atomic disorder during the
8 deposition process include:

9 - a low substrate temperature, that is maintaining the surface to be coated at a
10 temperature such that the ratio of the substrate temperature to the melting point of the metal
11 (in degrees Kelvin) is less than about 0.5, more preferably less than about 0.35 and most
12 preferably less than about 0.3; and optionally one or both of:

13 - a higher than normal working (or ambient) gas pressure, i.e. for vacuum
14 evaporation: e-beam or arc evaporation, greater than 0.01 mT, gas scattering evaporation
15 (pressure plating) or reactive arc evaporation, greater than 20 mT; for sputtering: greater than
16 75 mT; for magnetron sputtering: greater than about 10 mT; and for ion plating: greater than
17 about 200 mT; and

18 - maintaining the angle of incidence of the coating flux on the surface to be
19 coated at less than about 75°, and preferably less than about 30°

20 The metals used in the coating are those known to release ions etc. having an anti-
21 microbial effect, as set out above. For most medical devices, the metal must also be
22 biocompatible. Preferred metals include the noble metals Ag, Au, Pt, Pd, and Ir as well as
23 Sn, Cu, Sb, Bi, and Zn or alloys or compounds of these metals or other metals. Most
24 preferred is Ag or Au, or alloys or compounds of one or more of these metals.

25 A thin film is formed on at least a part of the surface of the substrate/medical device.
26 For economic reasons, the film has a thickness no greater than that needed to provide release
27 of metal ions on a sustainable basis over a suitable period of time, and to generate the desired
28 interference colour. Within the preferred ranges of thicknesses set out above, the thickness
29 will vary with the particular metal in the coating (which varies the solubility and abrasion
30 resistance), and with the degree of atomic disorder in (and thus the solubility of) the coating.
31 The thickness will be thin enough that the coating does not interfere with the dimensional
32 tolerances or flexibility of the device for its intended utility.

1 The anti-microbial effect of the material so produced is achieved when the coated
2 substrate is brought into contact with an alcohol or a water based electrolyte such as, a body
3 fluid or body tissue, thus releasing metal ions, atoms, molecules or clusters. The
4 concentration of the metal species which is needed to produce an anti-microbial effect will
5 vary from metal to metal. Generally, anti-microbial effect is achieved in body fluids such as
6 plasma, serum or urine at concentrations less than about 0.5 - 5 µg/ml.

7 The ability to achieve release of metal atoms, ions, molecules or clusters on a
8 sustainable basis from a coating is dictated by a number of factors, including coating
9 characteristics such as composition, structure, solubility and thickness, and the nature of the
10 environment in which the device is used. As the level of atomic disorder is increased, the
11 amount of metal species released per unit time increases. For instance, a silver metal film
12 deposited by magnetron sputtering at $T/T_m < 0.5$ and a working gas pressure of about 7
13 mTorr releases approximately 1/3 of the silver ions that a film deposited under similar
14 conditions, but at 30 mTorr, will release over 10 days. Films that are created with an
15 intermediate structure (ex. lower pressure, lower angle of incidence etc.) have Ag release
16 values intermediate to these values as determined by bioassays. This then provides a method
17 for producing controlled release metallic coatings in accordance with this invention. Slow
18 release coatings are prepared such that the degree of disorder is low while fast release
19 coatings are prepared such that the degree of disorder is high.

20 For continuous, uniform coatings, the time required for total dissolution will be a
21 function of film thickness and the nature of the environment to which they are exposed. The
22 relationship in respect of thickness is approximately linear, i.e. a two fold increase in film
23 thickness will result in about a two fold increase in longevity.

24 It is also possible to control the metal release from a coating by forming a thin film
25 coating with a modulated structure. For instance, a coating deposited by magnetron
26 sputtering such that the working gas pressure was low (ex. 15 mTorr) for 50% of the
27 deposition time and high (ex. 30 mTorr) for the remaining time, has a rapid initial release of
28 metal ions, followed by a longer period of slow release. This type of coating is extremely
29 effective on devices such as urinary catheters for which an initial rapid release is required to
30 achieve immediate anti-microbial concentrations followed by a lower release rate to sustain
31 the concentration of metal ions over a period of weeks.

32 The substrate temperature used during vapour deposition should not be so low that

1 annealing or recrystallization of the coating takes place as the coating warms to ambient
2 temperatures or the temperatures at which it is to be used (ex. body temperature). This
3 allowable ΔT , that the temperature differential between the substrate temperature during
4 deposition and the ultimate temperature of use, will vary from metal to metal. For the most
5 preferred metals of Ag and Au, preferred substrate temperatures of -20 to 200°C, more
6 preferably -10°C to 100°C are used.

7 Atomic order may also be achieved, in either or both of the base and top layers 2, 4 in
8 accordance with the present invention, by preparing composite metal materials, that is
9 materials which contain one or more anti-microbial metals in a metal matrix which includes
10 atoms or molecules different from the anti-microbial metals.

11 Our preferred technique for preparing a composite material is to co- or sequentially
12 deposit the anti-microbial metal(s) with one or more other inert, biocompatible metals
13 selected from Ta, Ti, Nb, Zn, V, Hf, Mo, Si, Al and alloys of these metals or other metal
14 elements, typically other transition metals. Such inert metals have a different atomic radii
15 from that of the anti-microbial metals, which results in atomic disorder during deposition.
16 Alloys of this kind can also serve to reduce atomic diffusion and thus stabilize the disordered
17 structure. Thin film deposition equipment with multiple targets for the placement of each of
18 the anti-microbial and inert metals is preferably utilized. When layers are sequentially
19 deposited the layer(s) of the inert metal(s) should be discontinuous, for example as islands
20 within the anti-microbial metal matrix. The final ratio of the anti-microbial metal(s) to inert
21 metal(s) should be greater than about 0.2. The most preferable inert metals are Ti, Ta, Zn and
22 Nb. It is also possible to form the anti-microbial coating from oxides, carbides, nitrides,
23 sulphides, borides, halides or hydrides of one or more of the anti-microbial metals and/or one
24 or more of the inert metals to achieve the desired atomic disorder.

25 Another composite material within the scope of the present invention is formed by
26 reactively co- or sequentially depositing, by physical vapour techniques, a reacted material
27 into the thin film of the anti-microbial metal(s). The reacted material is an oxide, nitride,
28 carbide, boride, sulphide, hydride or halide of the anti-microbial and/or inert metal, formed in
29 situ by injecting the appropriate reactants, or gases containing same, (ex. air, oxygen, water,
30 nitrogen, hydrogen, boron, sulphur, halogens) into the deposition chamber. Atoms or
31 molecules of these gases may also become absorbed or trapped in the metal film to create
32 atomic disorder. The reactant may be continuously supplied during deposition for

codeposition or it may be pulsed to provide for sequential deposition. The final ratio of anti-microbial metal(s) to reaction product should be greater than about 0.2. Air, oxygen, nitrogen and hydrogen are particularly preferred reactants.

The above deposition techniques to prepare composite coatings may be used with or without the conditions of lower substrate temperatures, high working gas pressures and low angles of incidence previously discussed. One or more of these conditions are preferred to retain and enhance the amount of atomic disorder created in the coating.

It may be advantageous, prior to depositing an anti-microbial in accordance with the present invention, to provide an adhesion layer on the substrate or medical device to be coated, as is known in the art. For instance, for a latex device, a layer of Ti, Ta or Nb may be first deposited to enhance adhesion of the subsequently deposited anti-microbial coating. If Ta is used, a barrier layer such as tantalum oxide formed by anodization may be needed, as set out above.

2. Wound Dressings

The wound dressing in accordance with the invention includes at least two, and preferably at least three layers, laminated together by ultrasonic welding. A three layer wound dressing in accordance with the invention is shown generally at 10 in Figure 2 to include a first layer 12, which will be wound facing in use, a second layer 14, which preferably forms an absorbent core, and a third, optional layer 16, which forms the outer layer. The layers 12, 14 (and optionally 16) are laminated together by ultrasonic welds 18 at intermittent locations across the dressing 10.

A) Wound Facing Layer

The first layer 12 of the wound dressing 10 is formed of a perforated, preferably non-adherent material which allows for fluids to penetrate or diffuse therethrough in either or both directions. The perforated material may be formed of a woven or non-woven, non-woven being preferred, fabric such as cotton, gauze, a polymeric film such as polyethylene, nylon, polypropylene or polyester, an elastomer such as polyurethane or polybutadiene elastomers, or a foam such as open cell polyurethane foam. Exemplary perforated, non-adherent materials useful for the wound dressing include non-woven meshes such as DELNET™ P530, which is a non-woven wound veil formed of high density polyethylene using extrusion, embossing and orientation processes, produced by Applied Extrusion Technologies, Inc. Of Middletown, Delaware, USA. This same product is available as Exu-Dry CONFORMANT

1 2TM Wound Veil, from Frass Survival Systems, Inc., Bronx, New York, USA as a subset of
2 that company's Wound Dressing Roll (Non-Adherent) products. Other useful non-woven
3 meshes include CARELLETM or NYLON 90TM, available from Carolina Formed Fabrics
4 Corp., N-TERFACETM, available from Winfield Laboratories, Inc., of Richardson, Texas,
5 USA. Exemplary woven meshes may be formed from fibreglass or acetate, or cotton gauze.
6 An exemplary hydrophilic polyurethane foam is HYPOLTM, available from W.R. Grace &
7 Co., New York, NY, USA.

8 As set out more fully below in respect of the ultrasonic welding technique, at least one
9 of the first and second layers 12, 14 is formed from a polymeric material which is amenable
10 to ultrasonic welding, that is which will melt on the application of localized heat and then
11 fuse the layers together on cooling.

12 B) Absorbent Layer

13 The second, absorbent layer is formed from an absorbent material for absorbing
14 moisture from the wound, or as in the case of a burn wound dressing, for holding moisture
15 next to the wound. Preferably, the absorbent material is an absorbent needle punched non-
16 woven rayon/polyester core such as SONTARATM 8411, a 70/30 rayon/polyester blend
17 commercially available from Dupont Canada, Mississauga, Ontario, Canada. This product is
18 sold by National Patent Medical as an American White Cross sterile gauze pad. However,
19 other suitable absorbent materials include woven or non-woven materials, non-woven being
20 preferred made from fibers such as rayon, polyester, rayon/polyester, polyester/cotton, cotton
21 and cellulosic fibers. Exemplary are creped cellulose wadding, an air felt of air laid pulp
22 fibers, cotton, gauze, and other well known absorbent materials suitable for wound dressings.

23 C) Outer Layer

24 The third layer 16 of the wound dressing 10 is optional, but is preferably included to
25 regulate moisture loss, or to act as a barrier layer (for example for moisture, oxygen
26 penetration), to carry an anti-microbial coating, or alternatively to act as an adhesive layer to
27 anchor the wound dressing around the wound. In the case of burn wound dressings, the third
28 layer 16 is preferably formed of perforated, non-adherent material such as used in the first
29 layer 12. This allows moisture penetration as sterile water and the like are added.

30 D) Additional Optional Layers

31 Additional layers (not shown) may be included between or above the first, second and
32 third layers 12, 24, 16, as is well known in wound dressings. Thus the use of the terms first,

1 second and third layer, as used herein and in the claims is not meant to exclude such
2 additional layers.

3 E) Ultrasonic Welding

4 The first and second layers (and preferably the third layer, if present) are laminated
5 together at intermittent spaced locations across the dressing 10 by ultrasonic welds 18.
6 Ultrasonic welding is a known technique in the quilting art, and thus will not be discussed at
7 length. Briefly, heat (generated ultrasonically) and pressure are applied to either side of the
8 dressing 10 at localized spots through an ultrasonic horn so as to cause melting of at least one
9 of the plastic materials in the first and second layers 12, 14, and the subsequent bonding
10 together of the layers on cooling. The welds appear at localized circular spots and are
11 preferably less than 0.5 cm in diameter. If the third layer 16 is present, the ultrasonic welding
12 can be performed from either side of the dressing, and will bind all three layers 12, 14 and 16
13 together.

14 The use of ultrasonic welding of the layers at spaced locations has the advantage of
15 retaining the absorbent and moisture penetration properties of the layers 12, 14, while
16 retaining the conforming properties of the dressing. Edge seams, stitching and adhesives
17 have the disadvantage of interfering with one or more of these desirable properties of wound
18 dressings. Furthermore, by spacing the welds 18 at intermittent locations across the dressing,
19 the wound dressing may be cut to smaller sizes, as needed, without causing delamination.
20 Preferred spacings of about 2.5 cm between welds allows the dressing to be cut down to
21 about 2.5 cm sizes, while maintaining at least one weld to hold the laminated layers together.

22 F) Anti-Microbial Coatings On Wound Dressings

23 The wound dressing of this invention preferably includes an anti-microbial coating
24 formed from an anti-microbial metal. The coating is applied to one or more of the layers 12,
25 14, 16, but is most preferably applied at least to the first, wound facing layer 12 to provide a
26 localized anti-microbial effect next to the wound. The coating may also be applied to the
27 outer layer 16 for additional anti-microbial effect.

28 The coating is most preferably formed with atomic disorder in accordance with the
29 procedures set out above and as described in US Patent 5,454,886. Most preferably, the
30 coating is formed as a multilayer anti-microbial coating, as set above, to produce an
31 interference colour. In this way, the coating provides not only an anti-microbial effect to
32 limit infection, but also acts as an indicator of activation of the dressing. As the top layer of

1 the coating is activated by contacting an electrolyte such as wound exudate, blood or added
2 water, even minor dissolution of the anti-microbial metal results in a detectable colour
3 change, indicating that an anti-microbial effect is being provided. If there is no colour
4 change, additional moisture might be provided to the coating by adding water, until a colour
5 change is detected. In the treatment of burn wounds with the wound dressings of this
6 invention, wound exudates are usually sufficient to activate the coating. Once activated, the
7 dressing should be maintained in a moist condition by the addition of sterile water if
8 necessary.

9 G) Sterilization and Packaging of Wound Dressings

10 Wound dressings with anti-microbial coatings of an anti-microbial metal formed with
11 atomic disorder are preferably sterilized without applying excessive thermal energy, which
12 can anneal out the atomic disorder, thereby reducing or eliminating a useful anti-microbial
13 effect. Gamma radiation is preferred for sterilizing such wound dressings, as discussed in US
14 Patent 5,454,886.

15 It should be appreciated that the use of ultrasonic welding to laminate the layers of
16 wound dressings with anti-microbial coatings formed from anti-microbial metals with atomic
17 disorder is advantageous since it achieves bonding in localized spots and avoids applying heat
18 to any significant portion of the dressing, thereby avoiding any significant reduction in the
19 anti-microbial effect through annealing out of atomic disorder.

20 The sterilized wound dressings should be sealed in air tight packaging which excludes
21 light penetration to avoid additional oxidation of the anti-microbial coating. Metallized
22 polyester peelable pouches are preferred. The shelf life of anti-microbial wound dressings
23 thus sealed is over one year.

24 H) Burn Wound Treatment

25 Animal and human trials with the burn wound dressing of the present invention,
26 carrying a bi-layer anti-microbial coating formed with silver having atomic disorder,
27 manufactured as set out above and as described in greater detail in Example 3, have shown
28 excellent results in controlling infection. In addition, the anti-microbial metal coating has
29 been found to improve how well the dressing handles, reducing static and adding weight to
30 the dressing to keep it in place during treatment and wrapping. In use, the dressings are kept
31 moist, at 100% relative humidity. Wound exudate may be sufficient in itself to maintain this
32 humidity level. Otherwise, adding sterile water, for instance three times daily has been found

1 to be sufficient. The wound dressing is thereafter wrapped in a known manner to keep the
2 wound moist and clean. Dressings are changed as required for wound observation and
3 cleaning, but need not be changed more frequently than every 24 hours, and can provide an
4 anti-microbial effect for a much longer period of time.

5 1) Advantages

6 Advantages of such burn wound dressings against conventional burn wound treatment
7 regimes are set out below.

8 i) The amount of Ag^+ or silver species in solution adjacent the dressing is
9 controlled by the concentration of Ag^+ in equilibrium in the solution at 60 - 100 $\mu\text{g}/\text{ml}$, which
10 is sufficient to provide a sustainable anti-microbial effect for a considerable period of time.
11 The use of a 0.5% solution of silver nitrate applied 12 times daily, provides a cumulative
12 exposure to silver ions of 61,000 $\mu\text{g}/\text{in}^2/\text{day}$ (calculated assuming an 8 ply dressing with
13 absorptive capacity of 200 $\mu\text{L}/\text{in}^2$ per ply). A comparable calculation for silver coated
14 dressings of this invention, assuming a wound weep maximum of 8 $\text{ml}/\text{in}^2/\text{day}$ is 800
15 $\mu\text{g}/\text{in}^2/\text{day}$.

16 ii) Compared to silver nitrate treatments, the silver coated burn wound dressings
17 of this invention eliminates staining from silver nitrate, leaving patients and relatives less
18 shocked by discoloration at the injury site, and reducing the cleaning costs of the hospital (for
19 bedding, flooring etc.).

20 iii) With silver nitrate treatment, the Ag^+ ion complexes with chloride ions at the
21 wound dressing interface to form a non anti-microbial zone. The silver coated wound
22 dressings of this invention provide a sustained release of silver species at a controlled and
23 non-excessive equilibrium concentration, ensuring that silver species remain available at the
24 wound interface.

25 iv) The absorbent core of the wound dressing maintains a high relative humidity
26 at the wound site, to maintain an anti-microbial effect and to minimize drying and desiccation
27 of new cell growth. The absorbent core also provides an "anti-microbial zone" above the
28 wound, which extends through the thickness of the dressing to create a sufficient
29 residence/exposure time for migrating microbes to ensure that they are killed. This is unlike
30 silver nitrate treatment in which there is no replacement of the silver ion at the wound surface
31 after it is consumed by chloride ions or proteins (excluding the possibility of diffusion).

32 v) The wound dressing needs minimal to no wetting (no more than 3 times daily),

limiting the hypothermia problem encountered with silver nitrate treatments which require 12 times daily wetting and the cleaning needed when silver sulphadiazine creams are used.

vi) The silver coating on the wound dressing materials has been found to be non-adherent, and thus less disruptive to wound healing than dressings that adhere, as are often used in silver nitrate treatments.

viii) The silver coated wound dressing of this invention, produced with an interference colour and a top layer which releases silver ions etc. on contact with an electrolyte, provides a visible colour change to demonstrate that the anti-microbial metal film has been activated and that silver species are being released.

3. Examples

The invention is further illustrated by the following non-limiting examples.

Example 1

This example is included to demonstrate multilayer colour coatings on various reflective base layers covered with anti-microbial silver top layers in order to generate first and second order interference colours. Bi-layer metal coatings were produced by magnetron sputtering onto glass coverslips base layers of Ag, Ta or Au and covering with top layers of Ag under the sputtering conditions set out in Table 1. To demonstrate Al as a base layer, the top Ag layer was sputtered onto Al foil, the Ag sputtering conditions being as set out in Table 1.

Table 1

<u>Sputtering Conditions:</u>	<u>Base Layer</u>	<u>Top Layer</u>
Target	99.99% Ag, Ta, Au	99.99% Ag
Target Size	20.3 cm diameter	20.3 cm diameter
Working Gas	100 wt% Ar	99/1 wt% Ar/O ₂
Working Gas Pressure	40 mTorr	40 mTorr
Power	0.1 kW	0.05 kW
Substrate Temperature	20°C	20°C
Base Pressure	2.0 X 10 ⁻⁶ Torr	2.0 X 10 ⁻⁶ Torr
Anode/Cathode Distance	100mm	100mm
Sputtering Time/Film Thickness	Ta - 16 min, 220 nm Ag - 8 min, 200 nm Au - 9 min, 200 nm	1 - 10 min, 10 - 100 nm
Voltage	Ta - 193 V Ag - 291 V Au - 322 V	295 V

The thickness of the top layer was varied, as set out in Table 2 below. The base layers of Ag, Ta, and Au had thicknesses of 200 nm. The resulting bilayer coatings had the appearances as set out in Table 2.

Table 2

Top Layer Thickness:	Base Layer Ag 99/1% Ar/O ₂ Colour: Bronze	Base Layer Ag 100 % Ar Colour: Silver	Base Layer Ta 100 % Ar Colour: Grey	Base Layer Au 100 % Ar Colour: Gold
10 nm	Bronze/Red	Pale Red	Light Grey	Yellow/Orange
20 nm	Purple	Pink/Yellow	Silver	Auburn
30 nm	Blue/Purple	Light Purple	Silver	Blue
40 nm	Light Blue	Grey/Blue	Gold to Silver	Turquoise
50 nm	Lt Blue/Yellow	Silver	Purple to Silver	Teal
60 nm	Light Yellow	Light Yellow	Blue to Silver	Lt Blue/Green
70 nm	Bronze	Lt Green/Yellow	Blue to Silver	Yellow
80 nm	Purple	Light Pink	Olive to Grey	Green/Yellow
90 nm	Purple/Pink	Pink	Olive to Grey	Olive
100 nm	Aquamarine	Aqua/Pink	Pink to Grey	Lt Pink/Yellow

The coatings formed on Ta metal changed to silver or grey within about 10 minutes of sputtering, indicating the need for a barrier layer to prevent reduction of the top layer to Ag base metal.

When a silver top layer was sputtered onto Al foil samples, under conditions as set out above, but in 96/4 wt % Ar/O₂ at 0.15 kW, a blue interference colour was observed.

Sputtering conditions were varied for the Ag base layer samples by changing the working gas to 96/4 wt % Ar/O₂, and depositing a 900 nm film, then covering with a top layer of Ag sputtered in 96/4 wt % Ar/O₂ at 0.15 kW, V = 346 V, for about 1, 1.5 and 2.25 min. to achieve about 67, 100, 140 nm films. All other conditions were as set out in Table 1. Interference colours produced were purple, blue and yellow respectively.

1 Example 2

2 This example is included to demonstrate a bilayer anti-microbial silver coating on a
 3 wound dressing material. A high density polyethylene wound dressing, CONFORMANT 2™
 4 was coated with a silver base layer and a silver/oxide top layer to generate a coloured anti-
 5 microbial coating having indicator value. The coating layers were formed by magnetron
 6 sputtering under the conditions set out in Table 3.

7 Table 3

8 <u>Sputtering Conditions:</u>	<u>Base Layer</u>	<u>Top Layer</u>
9 Target	99.99% Ag	99.99% Ag
10 Target Size	20.3 cm diameter	20.3 cm diameter
11 Working Gas	96/4 wt% Ar/O ₂	96/4 wt% Ar/O ₂
12 Working Gas Pressure	40 mTorr	40 mTorr
13 Power	0.3 kW	0.15 kW
14 Substrate Temperature	20°C	20°C
15 Base Pressure	3.0 X 10 ⁻⁶ Torr	3.0 X 10 ⁻⁶ Torr
16 Anode/Cathode Distance	100mm	100mm
17 Sputtering Time	7.5 - 9 min	1.5 min
18 Voltage	369 - 373 V	346 V

19 The resulting coating was blue in appearance. A fingertip touch was sufficient to
 20 cause a colour change to yellow. The base layer was about 900 nm thick, while the top layer
 21 was 100 nm thick.

22 A zone of inhibition test was conducted. Mueller Hinton agar was dispensed into
 23 Petri dishes. The agar plates were allowed to surface dry prior to being inoculated with a
 24 lawn of *Staphylococcus aureus* ATCC#25923. The inoculant was prepared from Bactrol
 25 Discs (Difco, M.) Which were reconstituted as per the manufacturer's directions.
 26 Immediately after inoculation, the coated materials to be tested were placed on the surface of
 27 the agar. The dishes were incubated for 24 hr. at 37°C. After this incubation period, the
 28 zone of inhibition was calculated (corrected zone of inhibition = zone of inhibition - diameter
 29 of the test material in contact with the agar). The results showed a corrected ZOI of about 10
 30 mm.

31 The coating was analyzed by nitric acid digestion and atomic absorption analysis to
 32 contain 0.24 +/- 0.04 mg silver per mg high density polyethylene. The coating is a binary
 33 alloy of silver (>97%) and oxygen with negligible contaminants, based on secondary ion
 34 mass spectroscopy. The coating, as viewed by SEM, was highly porous and consisted of
 35 equiaxed nanocrystals organized into coarse columnar structures with an average grain size of

1 10 nm. Silver release studies demonstrated that silver was released continuously from the
2 coating until an equilibrium concentration of about 66 mg/L was reached (determined by
3 atomic absorption), a level that is 50 to 100 times higher than is expected from bulk silver
4 metal (solubility ≤ 1 mg/L).

5 By varying the coating conditions for the top layer to lengthen the sputtering time to 2
6 min, 15 sec., a yellow coating was produced. The top layer had a thickness of about 140 nm
7 and went through a colour change to purple with a fingertip touch. Similarly, a purple
8 coating was produced by shortening the sputtering time to 1 min, to achieve a top layer
9 thickness of about 65 nm. A fingertip touch caused a colour change to yellow.

10 Example 3

11 This example is included to demonstrate a multilayer burn wound dressing in
12 accordance with the present invention. High density polyethylene mesh dressing material
13 CONFORMANT 2TM dressing was coated with a bilayer blue anti-microbial coating as set
14 forth in Example 2, using the sputtering conditions of Table 3. Two layers of this coated
15 dressing material were placed above and below an absorbent core material formed from
16 needle punched rayon/polyester (SONTARATM 8411). The first, wound facing layer of
17 coated polyethylene was oriented with the blue coating side down, while the third, outer layer
18 of coated polyethylene was oriented with the blue coating facing inwardly toward the
19 absorbent core. The three layers were laminated together by ultrasonic welding to produce
20 welds between all three layers spaced at about 2.5 cm intervals across the dressing. This
21 allowed the wound dressing to be cut down to about 2.5 cm size portions for the treatment of
22 smaller wounds, while still providing at least one weld in the dressing portion.

23 The coated dressings were sterilized using gamma radiation and a sterilization dose of
24 25 kGy. The finished dressing was packaged in sealed individually metallized polyester
25 peelable pouches, and has shown a shelf life greater than 1 year in this form.

26 The absorptive capacity and moisture content of the finished dressing was tested to
27 ensure that the dressing maintained the capability to absorb after coating. Packaged, sterile
28 dressings were tested and compared to uncoated, untreated control dressings. The absorptive
29 capacity of the test dressings was 7.36 g of distilled water and 7.32 g of 1.23 sodium nitrate,
30 compared to absorption by the control dressings of 7.76 g and 7.45 g respectively, indicating
31 similar uptakes by both materials. The drop penetration of the coated dressings was tested
32 and was found not to differ from the control dressings. The moisture content was 4.1% and

1 3.6% for the coated dressing and for the untreated controls respectively. Based on these
2 results, it was concluded that the coating of the present invention does not alter the moisture
3 related properties of the dressing.

4 A clinical study with 30 human patients with various degree burn wounds using the
5 above coated wound dressings has demonstrated an ability to decrease burn wound
6 "infection" (4 org./50 biopsies for the dressing of this invention vs. 16 org./50 biopsies for
7 silver nitrate treatment), the dressings being changed every 24 hours and being kept at 100%
8 relative humidity by the application of sterile water 3 times daily, compared to a control burn
9 wound treatment with 0.5% solutions of silver nitrate applied 12 times daily, dressings being
10 changed every 24 hours. In the above, "infection" means greater than 1×10^5 colony forming
11 units/g tissue.

12 Example 4

13 This example is included to demonstrate an anti-microbial material with an in situ
14 generated top layer on contact with an alcohol or a water based electrolyte in order to cause a
15 colour change through the generation of an interference colour. A single layer anti-microbial
16 coating was produced by magnetron sputtering onto high density polyethylene wound
17 dressing using the base layer as set out in Example 3, the sputtering conditions being those set
18 out in Table 3 of Example 2. The resulting coating was about 900 nm thick and bronze in
19 appearance. The coating was wetted with a wet fingertip touch (saliva), causing the colour of
20 the coating to change to blue.

21 Without being bound by the same, it is believed that the colour change was the result
22 of the in situ generation of a thin film meeting the description of a reflective and light
23 transmissive top layer as set out above, over a reflective base layer, thus creating the
24 conditions necessary for producing an interference colour. The mechanism is believed to be
25 as follows. The water on the coating caused a change in both the thickness of the coating and
26 the composition of a thin top layer of the coating, thereby creating a thin top layer which had
27 a different refractive index from the underlying coating. Water from the fingertip was
28 sufficient to displace air in the surface pores of the film (which is known from SEM to be
29 porous), initiating both dissolution of the film and changing the refractive index of the thin
30 layer. The blue interference colour resulted from the incident light reflecting off both the
31 air/thin layer interface and the thin layer/base layer interface and recombining to create a
32 changed, blue colour.

1 All publications mentioned in this specification are indicative of the level of skill of
2 those skilled in the art to which this invention pertains. All publications are herein
3 incorporated by reference to the same extent as if each individual publication was specifically
4 and individually indicated to be incorporated by reference.

5 The terms and expressions in this specification are, unless otherwise specifically
6 defined herein, used as terms of description and not of limitation. There is no intention, in
7 using such terms and expressions, of excluding equivalents of the features illustrated and
8 described, it being recognized that the scope of the invention is defined and limited only by
9 the claims which follow.

1 We claim:

2 1. A multilayer anti-microbial material comprising:

3 a base layer of a partly reflective material capable of generating an interference colour
4 when covered with a partly reflective, partly light transmissive top layer;

5 a top layer formed over said base layer, said top layer being a partly reflective, partly
6 light transmissive thin film containing at least one anti-microbial metal and having a
7 thickness such that an interference colour is produced, said top layer having a refractive index
8 different from that of the base layer, and the anti-microbial metal being formed with sufficient
9 atomic disorder such that the top layer, in contact with an alcohol or water based electrolyte,
10 releases ions, atoms, molecules or clusters of the anti-microbial metal into the alcohol or
11 water based electrolyte at a concentration sufficient to provide a localized anti-microbial
12 effect on a sustainable basis.

13 2. The material of claim 1, wherein the material in the base layer is a metal selected from
14 the group consisting of Ag, Au, Pt, Pd, Cu, Ta, Al and alloys or compounds of one or more of
15 these metals, in a partly reflective form.

16 3. The material of claim 2, wherein the anti-microbial metal in the top layer is selected
17 from the group consisting of Ag, Au, Pt, Pd, Ir, Sn, Cu, Sb, Bi, Zn, and alloys or compounds
18 of one or more of these metals.

19 4. The material of claim 3, wherein the material in the base layer and the anti-microbial
20 metal in the top layer is a metal selected from the group consisting of Au, Ag, Pt, Pd, and Cu
21 in a partly reflective form, and is formed by vapour deposition with sufficient atomic disorder
22 such that the top layer, in contact with an alcohol or water based electrolyte, releases ions,
23 atoms, molecules or clusters of the anti-microbial metal into the alcohol or water based
24 electrolyte at a concentration sufficient to provide a localized anti-microbial effect on a
25 sustainable basis.

26 5. The material of claim 4, wherein the metal in the base layer and top layer is Ag, Pt or
27 Au.

28 6. The material of claim 4, wherein the top layer is a thin film of a composite material
29 formed by co-, sequentially or reactively depositing the anti-microbial metal by vapour
30 deposition in a matrix with atoms or molecules of a different material to create atomic
31 disorder in the matrix, said different material being selected from the group consisting of
32 biocompatible metals, oxygen, nitrogen, hydrogen, boron, sulphur or halogens, or an oxide,

1 nitride, carbide, boride, halide, sulphide or hydride of either or both of an anti-microbial
2 metal or a biocompatible metal.

3 7. The material of claim 6, wherein the biocompatible metal is selected from the group
4 consisting of Ta, Ti, Nb, V, Hf, Zn, Mo, Si and Al, and wherein the anti-microbial metal is
5 selected from the group consisting of Ag, Au, Pt, Pd, and Cu.

6 8. The material of claim 6, wherein the anti-microbial metal is silver and said different
7 material is one or both of silver oxide and atoms or molecules containing oxygen trapped or
8 absorbed in the matrix.

9 9. The material of claim 1, wherein the top layer is less than 400 nm thick, and the base
10 layer is at least 25 nm thick.

11 10. The material of claim 8, wherein the top layer is between 5 and 210 nm thick, and the
12 base layer is at least 60 nm thick.

13 11. The material of claim 8, wherein the top layer is about 40 - 160 nm thick and the base
14 layer is at least about 300 nm thick.

15 12. The material of claim 1, wherein the base and top layers are provided on a medical
16 device.

17 13. The material of claim 10, wherein the base and top layers are provided on a wound
18 dressing.

19 14. A process for producing a multilayer anti-microbial material capable of indicating
20 exposure to an alcohol or water based electrolyte, comprising:

21 providing a base layer of a partly reflective material capable of generating an
22 interference colour when covered with a partly reflective, partly light transmissive top layer;

23 providing a top layer over said base layer, said top layer being a partly reflective,
24 partly light transmissive thin film containing at least one anti-microbial metal and having a
25 thickness such that an interference colour is produced, said top layer having a refractive index
26 different from that of the base layer, and said anti-microbial metal being formed with
27 sufficient atomic disorder such that the top layer, in contact with an alcohol or water based
28 electrolyte, releases ions, atoms, molecules or clusters of the anti-microbial metal into the
29 alcohol or water based electrolyte at a concentration sufficient to provide a localized anti-
30 microbial effect on a sustainable basis.

31 15. The process of claim 14, wherein the material in the base layer is a metal selected
32 from the group consisting of Ag, Au, Pt, Pd, Cu, Ta, Al and alloys or compounds of one or

1 more of these metals, in a partly reflective form.

2 16. The process of claim 15, wherein the anti-microbial metal in the top layer is selected
3 from the group consisting of Ag, Au, Pt, Pd, Ir, Sn, Cu, Sb, Bi, Zn, and alloys or compounds
4 of one or more of these metals.

5 17. The process of claim 16, wherein the material in the base layer and the anti-microbial
6 metal in the top layer is a metal selected from the group consisting of Au, Ag, Pt, Pd, and Cu
7 in a partly reflective form, and is formed by vapour deposition with sufficient atomic disorder
8 such that the top layer, in contact with an alcohol or water based electrolyte, releases ions,
9 atoms, molecules or clusters of the anti-microbial metal into the alcohol or water based
10 electrolyte at a concentration sufficient to provide a localized anti-microbial effect on a
11 sustainable basis.

12 18. The process of claim 17, wherein the metal in the base and top layer is Ag, Pt or Au.

13 19. The process of claim 17, wherein the top layer is a thin film of a composite material
14 formed by co-, sequentially or reactively depositing the anti-microbial metal by vapour
15 deposition in a matrix with atoms or molecules of a different material to create atomic
16 disorder in the matrix, said different material being selected from the group consisting of
17 biocompatible metals, oxygen, nitrogen, hydrogen, boron, sulphur or halogens, or an oxide,
18 nitride, carbide, boride, halide, sulphide or hydride of either or both of an anti-microbial
19 metal or a biocompatible metal.

20 20. The process of claim 19, wherein the biocompatible metal is selected from the group
21 consisting of Ta, Ti, Nb, V, Hf, Zn, Mo, Si, and Al, and wherein the anti-microbial metal is
22 selected from the group consisting of Ag, Au, Pt, Pd, and Cu.

23 21. The process of claim 19, wherein the anti-microbial metal is silver and said different
24 material is one or both of silver oxide and atoms or molecules containing oxygen trapped or
25 absorbed in the matrix.

26 22. The process of claim 14, wherein the top layer is less than 400 nm thick, and the base
27 layer is at least 25 nm thick.

28 23. The process of claim 19, wherein the top layer is between 5 and 210 nm thick, and the
29 base layer is at least 60 nm thick.

30 24. The process of claim 21, wherein the top layer is about 40 - 160 nm thick and the base
31 layer is at least about 300 nm thick.

32 25. The process of claim 14, wherein the base and top layers are provided on a medical

1 device.

2 26. The process of claim 23, wherein the base and top layers are provided on a wound
3 dressing.

4 27. A multilayer, laminated wound dressing, comprising:

5 a first, wound facing layer formed of a perforated, non-adherent material;

6 a second layer laminated to the first layer, and being formed of an absorbent material;

7 an optional third layer laminated to one or both of the first and second layers;

8 at least one of the first, second and optional third layers, being formed from a plastic
9 material; and

10 the first, second and optional third layers being laminated together by ultrasonic welds
11 spaced intermittently on the dressing so as to allow the dressing to be cut down in size
12 without causing delamination.

13 28. The wound dressing of claim 27, wherein the first layer, includes a coating containing
14 an anti-microbial metal.

15 29. The wound dressing of claim 27, wherein the first layer includes a thin film
16 containing at least one anti-microbial metal, said anti-microbial metal being formed with
17 sufficient atomic disorder such that the thin film, in contact with an alcohol or water based
18 electrolyte, releases ions, atoms, molecules or clusters of the anti-microbial metal into the
19 alcohol or water based electrolyte at a concentration sufficient to provide a localized anti-
20 microbial effect on a sustainable basis.

21 30. The wound dressing of claim 27, wherein the first layer includes a multilayer anti-
22 microbial coating comprising:

23 a base layer of a partly reflective material capable of generating an interference colour
24 when covered with a partly reflective, partly light transmissive top layer;

25 a top layer formed over said base layer, said top layer being a partly reflective, partly
26 light transmissive thin film containing at least one anti-microbial metal and having a
27 thickness such that a first or second order interference colour is produced, said top layer
28 having a refractive index different from that of the base layer, and anti-microbial metal being
29 formed with sufficient atomic disorder such that the top layer, in contact with an alcohol or
30 water based electrolyte, releases ions, atoms, molecules or clusters of the anti-microbial metal
31 into the alcohol or water based electrolyte at a concentration sufficient to provide a localized
32 anti-microbial effect on a sustainable basis.

- 1 31. The wound dressing of claim 30, wherein the multilayer anti-microbial coating is
2 provided on both the first and third layers, such that a colour change is detectable on either
3 side of the wound dressing.
- 4 32. The wound dressing of claim 30, wherein the material in the base layer is a metal
5 selected from the group consisting of Ag, Au, Pt, Pd, Cu, Ta, Al and alloys or compounds of
6 one or more of these metals, in a partly reflective form.
- 7 33. The wound dressing of claim 32, wherein the anti-microbial metal in the top layer is
8 selected from the group consisting of Ag, Au, Pt, Pd, Ir, Sn, Cu, Sb, Bi, Zn, and alloys or
9 compounds of one or more of these metals.
- 10 34. The wound dressing of claim 33, wherein the material in the base layer and the anti-
11 microbial metal in the top layer is a metal selected from the group consisting of Au, Ag, Pt,
12 Pd, and Cu in a partly reflective form, and is formed by vapour deposition with sufficient
13 atomic disorder such that the top layer, in contact with an alcohol or water based electrolyte,
14 releases ions, atoms, molecules or clusters of the anti-microbial metal into the alcohol or
15 water based electrolyte at a concentration sufficient to provide a localized anti-microbial
16 effect on a sustainable basis.
- 17 35. The wound dressing of claim 34, wherein the metal in the base and top layer is Ag, Pt
18 or Au.
- 19 36. The wound dressing of claim 33, wherein the top layer is a thin film of a composite
20 material formed by co-, sequentially or reactively depositing the anti-microbial metal by
21 vapour deposition in a matrix with atoms or molecules of a different material to create atomic
22 disorder in the matrix, said different material being selected from the group consisting of
23 biocompatible metals, oxygen, nitrogen, hydrogen, boron, sulphur or halogens, or an oxide,
24 nitride, carbide, boride, halide, sulphide or hydride of either or both of an anti-microbial
25 metal or a biocompatible metal.
- 26 37. The wound dressing of claim 36, wherein the biocompatible metal is selected from the
27 group consisting of Ta, Ti, Nb, V, Hf, Zn, Mo, Si and Al, and wherein the anti-microbial
28 metal is selected from the group consisting of Ag, Au, Pt, Pd, and Cu.
- 29 38. The wound dressing of claim 36, wherein the anti-microbial metal is silver and said
30 different material is one or both of silver oxide and atoms or molecules containing oxygen
31 trapped or absorbed in the matrix.
- 32 39. The wound dressing of claim 30, wherein the top layer is less than 400 nm thick, and

- 1 the base layer is at least 25 nm thick.
- 2 40. The wound dressing of claim 34, wherein the top layer is between 5 and 210 nm thick,
3 and the base layer is at least 60 nm thick.
- 4 41. The wound dressing of claim 38, wherein the top layer is about 40 - 160 nm thick and
5 the base layer is at least about 300 nm thick.
- 6 42. The wound dressing of claim 30, wherein the base and top layers are provided on a
7 medical device.
- 8 43. The wound dressing of claim 40, wherein the base and top layers are provided on a
9 wound dressing.
- 10 44. The wound dressing of claim 38, wherein the material in the base layer is a metal
11 selected from the group consisting of Au, Ag, Pt, Pd, and Cu in a partly reflective form, and
12 is formed by vapour deposition with sufficient atomic disorder such that the top layer, in
13 contact with an alcohol or water based electrolyte, releases ions, atoms, molecules or clusters
14 of the anti-microbial metal into the alcohol or water based electrolyte at a concentration
15 sufficient to provide a localized anti-microbial effect on a sustainable basis.
- 16 45. The wound dressing of claim 43, wherein the first and optional third layers are formed
17 from a non-woven, perforated, non-adherent high density polyethylene material.
- 18 46. The wound dressing of claim 45, wherein the second layer is formed from a non-
19 woven, absorbent rayon/polyester material.

1/1




Fig. 1.




Fig. 2.

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : A01N 59/16, G01N 21/45, A61L 15/18, 31/00, A61F 13/00	A3	(11) International Publication Number: WO 98/41095 (43) International Publication Date: 24 September 1998 (24.09.98)
(21) International Application Number: PCT/CA98/00102 (22) International Filing Date: 17 February 1998 (17.02.98) (30) Priority Data: 08/818,869 17 March 1997 (17.03.97) US (71) Applicant (for all designated States except US): WESTAIM TECHNOLOGIES INC. [CA/CA]; 10102 - 114 Street, Fort Saskatchewan, Alberta T8L 3W4 (CA). (72) Inventors; and (75) Inventors/Applicants (for US only): BURRELL, Robert, Ed- ward [CA/CA]; 52055, R.R. 221, Sherwood Park, Alberta T8E 1C6 (CA). PRECHT, Roderick, John [CA/CA]; 13143 - 34 Street, Edmonton, Alberta T5A 3K1 (CA). (74) Agent: McKAY-CAREY, Mary, Jane; McKay-Carey & Com- pany, 2125 Commerce Place, 10155 - 102nd Street, Edmon- ton, Alberta T5J 4G8 (CA).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, GM, GW, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims</i> <i>and to be republished in the event of the receipt of amendments.</i> (88) Date of publication of the international search report: 11 March 1999 (11.03.99)
(54) Title: ANTI-MICROBIAL COATINGS HAVING INDICATOR PROPERTIES AND WOUND DRESSINGS		
(57) Abstract <p>Multilayer anti-microbial materials formed to produce an interference colour, and thus an indicator of anti-microbial effect, are provided. The materials include a partly reflective base layer and a partly reflective, partly transmissive top layer balanced to produce an interference colour. The top layer is formed from an anti-microbial metal with atomic disorder. Dissolution or a change in composition of the top layer on contacting an alcohol or electrolyte causes a change in optical path length so as to produce a change in the interference colour of the material. Multilayer, laminated wound dressings are also provided. The dressing includes a first and second layer, and preferably a third layer. The first and third layers are formed of perforated, non-adherent materials and most preferably carry an anti-microbial coating as above. The second layer is sandwiched between the first and third layers and is formed of an absorbent material. At least one of the layers is formed from a plastic material. The layers are laminated together by ultrasonic welds spaced intermittently on the dressing to allow the dressing to be cut to size with delaminating.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

INTERNATIONAL SEARCH REPORT

Intern al Application No

PCT/CA 98/00102

A. CLASSIFICATION OF SUBJECT MATTER

IPC 6 A01N59/16 G01N21/45 A61L15/18 A61L31/00 A61F13/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 6 A01N A61L A61F G01N B29C B32B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 95 13704 A (WESTAIM TECHNOLOGIES INC ;BURRELL ROBERT EDWARD (CA); APTE PRASAD) 26 May 1995 see the whole document	1-46
X	see page 17, line 14 - page 18; examples 1,6,7,13,22 & US 5 454 886 A cited in the application	1,9-14, 22-26
A	WO 93 23092 A (WESTAIM TECHNOLOGIES INC ;BURRELL ROBERT EDWARD (CA); MORRIS LARRY) 25 November 1993 see the whole document	1-46
X	see page 9, line 26 - page 10, line 27; examples 1,6,7,13	1,9-14, 22-26
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

12 January 1999

Date of mailing of the international search report

21. 01. 99

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Muellners, W

INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 98/00102

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP 0 395 300 A (ALCAN INT LTD) 31 October 1990 see the whole document & US 5 124 172 A cited in the application ---	1-46
A	EP 0 430 608 A (SQUIBB & SONS INC) 5 June 1991 see page 2, line 20 - page 3, line 15 ---	1-46
A	DATABASE WPI Week 88201988 Derwent Publications Ltd., London, GB; AN 88-136448 XP002070661 & JP 63 078051 A (TEIJIN LTD) see abstract ---	1-46
A	WO 92 11043 A (Q LIFE SYSTEMS INC) 9 July 1992 see page 1 - page 6 ---	1-46
A	EP 0 255 248 A (MINNESOTA MINING & MFG) 3 February 1988 see page 2 - page 4, line 13 ---	1-46
X	GB 2 132 939 A (WYCOMBE MARSH PAPER MILLS LTD) 18 July 1984 see page 1, line 19 - line 22 see page 1, line 46 - line 60 see page 2, line 10 - line 29; claims ---	27
Y	GB 2 281 212 A (ROBINSON & SONS LTD) 1 March 1995 see page 1 - page 3 see page 4, last paragraph - page 5, paragraph 1 ---	27
Y	GB 2 298 612 A (BRITISH UNITED SHOE MACHINERY) 11 September 1996 see page 1, line 1 - line 33 see page 2, line 36 - page 3, line 9 see page 2, line 6 - line 19 see page 4, paragraph 16 - paragraph 30 ---	27
A	GB 2 121 355 A (POWNALL DAVID) 21 December 1983 see page 1, line 4 - line 38 see page 1, line 125 - page 2, line 1 ---	27-29
	-/--	

INTERNATIONAL SEARCH REPORT

Inter. Patent Application No.

PCT/CA 98/00102

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>US 5 030 302 A (JUD WILFRIED ET AL) 9 July 1991 see column 1, line 10 - line 21 see column 2, line 14 - line 68 see column 4, line 18 - line 39; figures 1,2</p> <p>-----</p>	27-29

INTERNATIONAL SEARCH REPORT

Intr tional application No.
PCT/CA 98/00102

Box I Observations where certain claims were found unsearchable (Continuation of item 1 of first sheet)

This International Search Report has not been established in respect of certain claims under Article 17(2)(a) for the following reasons:

1. ☐ Claims Nos.:
because they relate to subject matter not required to be searched by this Authority, namely:
2. ☐ Claims Nos.:
because they relate to parts of the International Application that do not comply with the prescribed requirements to such an extent that no meaningful International Search can be carried out, specifically:
3. ☐ Claims Nos.:
because they are dependent claims and are not drafted in accordance with the second and third sentences of Rule 6.4(a).

Box II Observations where unity of invention is lacking (Continuation of item 2 of first sheet)

This International Searching Authority found multiple inventions in this international application, as follows:

see additional sheet

1. ☒ As all required additional search fees were timely paid by the applicant, this International Search Report covers all searchable claims.
2. ☐ As all searchable claims could be searched without effort justifying an additional fee, this Authority did not invite payment of any additional fee.
3. ☐ As only some of the required additional search fees were timely paid by the applicant, this International Search Report covers only those claims for which fees were paid, specifically claims Nos.:
4. ☐ No required additional search fees were timely paid by the applicant. Consequently, this International Search Report is restricted to the invention first mentioned in the claims; it is covered by claims Nos.:

Remark on Protest

- ☐ The additional search fees were accompanied by the applicant's protest.
- ☒ No protest accompanied the payment of additional search fees.

FURTHER INFORMATION CONTINUED FROM PCT/ISA/ 210

This International Searching Authority found multiple (groups of) inventions in this international application, as follows:

1. Claims: 1-26 and 30-46 (all completely),
27-29 (all partially)

A multilayer antimicrobial material comprising:

- a) a base layer capable of generating interference colour when covered with a partly reflective, partly transmissive top layer,
 - b) such a top layer in a interference colouring generating thickness, having a refractive index different from that of the base layer, containing an antimicrobial metal in sufficient atomic disorder to provide in contact with alcohol or water based electrolytes a localized antimicrobial effect;
- a process for producing such a multilayer antimicrobial material
- a wound dressing comprising a layer coated with said multilayer antimicrobial material

2. Claims: 27-29 (all partially)

A multilayer, laminated wound dressing, comprising:

- a) a first layer of a perforated, non-adherent material
 - b) a second layer of an absorbent material
- the first and second and optional third layer, of which at least one is of a plastic material, are laminated together by ultrasonic welds spaced intermittently on the dressing so as to allow the dressing to be cut down in size without causing delamination.

INTERNATIONAL SEARCH REPORT

Information on patent family members

Interr. nat Application No

PCT/CA 98/00102

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9513704 A	26-05-1995	US 5454886 A	03-10-1995
		AU 8055194 A	06-06-1995
		BR 9408225 A	26-08-1997
		CA 2136454 A	19-05-1995
		CA 2136455 A	19-05-1995
		CN 1140977 A	22-01-1997
		EP 0729302 A	04-09-1996
		EP 0875146 A	04-11-1998
		HU 75526 A	28-05-1997
		JP 9505112 T	20-05-1997
		NZ 275066 A	24-09-1998
		PL 314683 A	16-09-1996
		ZA 9409085 A	16-05-1996
		US 5503704 A	02-04-1996
		CA 2136456 A	19-05-1995
		US 5837275 A	17-11-1998
WO 9323092 A	25-11-1993	US 5681575 A	28-10-1997
		AT 169829 T	15-09-1998
		AU 673170 B	31-10-1996
		AU 4055893 A	13-12-1993
		CA 2134217 A	25-10-1993
		CN 1082625 A	23-02-1994
		DE 69320472 D	24-09-1998
		DE 69320472 T	24-12-1998
		EP 0641224 A	08-03-1995
		ES 2119899 T	16-10-1998
		HU 69766 A	28-09-1995
		IL 105726 A	22-02-1998
		JP 8500392 T	16-01-1996
		MX 9302877 A	29-07-1994
		NZ 252076 A	24-02-1997
		US 5837275 A	17-11-1998
		US 5753251 A	19-05-1997
		US 5770255 A	23-06-1998
EP 0395300 A	31-10-1990	CA 1337173 A	03-10-1995
		AT 143731 T	15-10-1996
		DE 69028728 D	07-11-1996
		DE 69028728 T	06-03-1997
		DK 395300 T	02-12-1996
		JP 2300661 A	12-12-1990
		US 5124172 A	23-06-1992
EP 0430608 A	05-06-1991	AU 647421 B	24-03-1994
		AU 6573590 A	06-06-1991
		CA 2029172 A	29-05-1991
		DE 69016950 D	23-03-1995
		DE 69016950 T	14-06-1995
		JP 3182246 A	08-08-1991
		US 5181905 A	26-01-1993
WO 9211043 A	09-07-1992	CA 2033107 A	25-06-1992
		AU 669652 B	20-06-1996
		AU 9111491 A	22-07-1992
		EP 0564503 A	13-10-1993
		JP 6503736 T	28-04-1994
		US 5695857 A	09-12-1997

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 98/00102

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0255248	A	03-02-1988	US 4728323 A	01-03-1988
			AU 595333 B	29-03-1990
			AU 7427987 A	28-01-1988
			CA 1279573 A	29-01-1991
			DE 3780229 A	13-08-1992
			JP 2106690 C	06-11-1996
			JP 8024709 B	13-03-1996
			JP 63035260 A	15-02-1988
			KR 9506936 B	26-06-1995
			MX 165268 B	04-11-1992
GB 2132939	A	18-07-1984	NONE	
GB 2281212	A	01-03-1995	NONE	
GB 2298612	A	11-09-1996	NONE	
GB 2121355	A	21-12-1983	NONE	
US 5030302	A	09-07-1991	WO 8706525 A	05-11-1987
			EP 0264395 A	27-04-1988
			FI 875711 A	23-12-1987
			JP 63503131 T	17-11-1988